

## » BROOKHAVEN

**COLOR/CHARACTERISTICS:** Light gray with some buff variegation

**FEATURES:**

Stone is available for custom fabrication for architectural projects  
Random Height: 100% Split-face  
Dimensional: Sawn heights, split-face and ends

Available for both building and landscape stone applications.

**SPECIFICATIONS:**

**ASTM C 97**

SPECIFIC GRAVITY: 2.55

ABSORPTION: 2.66%

**ASTM C 99**

MODULUS OF RUPTURE: 1,866 lb/in<sup>2</sup>

**ASTM C 170**

COMPRESSIVE STRENGTH:

Perpendicular

Area 9.45 in<sup>2</sup>

13,350 psi

Parallel

Area 9.54 in<sup>2</sup>

12,800 psi

**ASTM C 880**

FLEXURAL STRENGTH:

Parallel to the Rift/Dry: 1,748 psi

Testing was performed in general accordance with the following ASTM Standards. This information is based in December 2017 test results by Professional Service Industries and Geotechnology.

\*C 99 and C 880 were performed under the dry condition, horizontal to the rift.

