

GUNSMOKE GRAY | FINISHES



Sawn Finish



Honed Finish



Polished Finish

BUSHHAMMER FINISH ALSO AVAILABLE JUST NOT PICTURED ABOVE

ASTM SPECIFICATIONS

ASTM C 97

SPECIFIC GRAVITY: 2.121

ABSORPTION: 6.13%

ASTM C 99

MODULUS OF RUPTURE: 801 psi

ASTM C 170

COMPRESSIVE STRENGTH: 8,138 psi
