

WESTON CREAM | FINISHES



Sawn Finish



Honed Finish



Polished Finish



Antique Brush Finish



Bushhammer Finish

ASTM SPECIFICATIONS

ASTM C 97

DENSITY: 135.61 lb/ft³

SPECIFIC GRAVITY: 2.173

ABSORPTION: 6.51%

ASTM C 99

MODULUS OF RUPTURE: 883 psi 6.09 Mpa

ASTM C 170

COMPRESSIVE STRENGTH: 5,686 psi 39.20 Mpa

ASTM C 241

ABRASION RESISTANCE: 5.06

ASTM C 880

FLEXURAL STRENGTH: Perpendicular: 1,053 psi Parallel: 7.26 Mpa
